



KuibyshevAzot  
古比雪夫氮(上海)工程塑料有限公司

## Technical data sheet

### Volgamid® PA66/6G33NC201

33% 玻璃纤维增强尼龙 66 尼龙 6 合金

33% glass fiber reinforced PA66/6 alloy

项目 Item	典型性能 Typical Characteristic	测试标准 Testing Standard
	值 Value	单位 Unit
<strong>机械性能 Mechanical Properties</strong>		
拉伸强度 Tensile Strength	202	MPa
断裂伸长率 Elongation at break		%
弯曲强度 Flexural Strength	265	MPa
弯曲模量 Flexural Modulus	8500	MPa
简支梁缺口冲击强度 Charpy Impact notched	14.3	KJ/m <sup>2</sup>
简支梁无缺口冲击强度 Charpy Impact unnotched	NB	KJ/m <sup>2</sup>
洛氏硬度 Rockwell Hardness	120	
<strong>热性能 Thermal Properties</strong>		
热变形温度 Temp. of deflection under load (0.45MPa)		°C
热变形温度 Temp. of deflection under load (1.80MPa)	244	°C
熔点 Melting Point		°C
<strong>电性能 Electrical Properties</strong>		
体积电阻率 Volume Resistant		ohm*m
表面电阻率 Surface Resistant		ohm
介电强度 Dielectric Strength		KV/mm
电痕化指数 Comp Track Index		V
<strong>其它 Others</strong>		
密度 Specific Gravity	1.38	g/cm <sup>3</sup>
灰分 Ash Content	33±2	%
吸水率 Water Absorption		%
模塑收缩率 Mold Shrinkage	0.3/0.8	%
<strong>燃烧性能</strong>		
UL 垂直燃烧 Flammability	HB	mm/Class
灼热丝可燃指数 Glow-wire Flammability Index		mm/°C
		IEC 60695-2-12

Disclaimer: Unless specified to the contrary, the value given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum value. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.