



KuibyshevAzot
古比雪夫氮(上海)工程塑料有限公司

Technical data sheet

Volgamid® PA6M30FRGY101

30%矿物填充阻燃尼龙 6

30%mineral filled flame-retardant PA6 without PBDE

项目 Item	典型性能 Typical Characteristic	测试标准 Testing Standard
	值 Value	单位 Unit
机械性能 Mechanical Properties		
拉伸强度 Tensile Strength	70 MPa	ISO527, 50mm/min
断裂伸长率 Elongation at break	2.5 %	ISO527, 50mm/min
弯曲强度 Flexural Strength	105 MPa	ISO178, 2mm/min
弯曲模量 Flexural Modulus	5500 MPa	ISO178, 2mm/min
简支梁缺口冲击强度	3.2 KJ/m ²	ISO179/1eA
Charpy Impact notched		
简支梁无缺口冲击强度	35 KJ/m ²	ISO179/1eU
Charpy Impact unnotched		
洛氏硬度 Rockwell Hardness	116	ISO2039/2
热性能 Thermal Properties		
热变形温度	°C	ISO75
Temp. of deflection under load (0.45MPa)		
热变形温度	120 °C	ISO75
Temp. of deflection under load (1.80MPa)		
熔点 Melting Point	°C	ISO3146C
电性能 Electrical Properties		
体积电阻率 Volume Resistant	ohm*m	IEC60093
表面电阻率 Surface Resistant	ohm	IEC60093
介电强度 Dielectric Strength	KV/mm	IEC 60243-1
电痕化指数 Comp Track Index	V	IEC 60112
其它 Others		
密度 Specific Gravity	1.53 g/cm ³	ISO1183
灰分 Ash Content	30-32 %	ISO3451-4
吸水率 Water Absorption	%	ISO62
模塑收缩率 Mold Shrinkage	0.4/0.6 %	ISO294-4
燃烧性能		
UL 垂直燃烧 Flammability	3.2/V0 mm/Class	UL-94
UL 垂直燃烧 Flammability	1.6/V2 mm/Class	UL-94
灼热丝可燃指数	960 mm/°C	IEC 60695-2-12
Glow-wire Flammability Index		

Disclaimer: Unless specified to the contrary, the value given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum value. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.